

Chemical Resistance Chart

Acetaldehyde - Alcohols (Propyl)

Chemical Resistance Data

These recommendations are based upon information from material suppliers and careful examination of available published information and are believed to be accurate. However, since the resistance of metals, plastics and elastomers can be affected by concentration, temperature, presence of other chemicals and other factors, this information should be considered as a general guide rather than an unqualified guarantee. Ultimately, the customer must determine the suitability of the pump used in various solutions.

All recommendations assume ambient temperatures unless otherwise noted.

RATINGS - CHEMICAL EFFECT

- A:** No effect - Excellent
- B:** Minor effect - Good
- C:** Moderate effect - Fair
- D:** Severe effect - Not Recommended

FOOTNOTES

1. P.V.C. - Satisfactory to 72° F.
2. Polypropylene - Satisfactory to 72° F.
3. Polypropylene - Satisfactory to 120° F.
4. Buna-N - Satisfactory for "O" Rings
5. Polyacetal - Satisfactory to 72° F.
6. Ceramag - Satisfactory to 72° F.

The ratings for these materials are based upon the chemical resistance only. Added consideration must be given to pump selections when the chemical is abrasive, viscous in nature, or has a Specific Gravity greater than 1.1

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy
Acetaldehyde ⁵	A	A	A	-	B	A	A	D	-	-	C	-	D	D	A	-	A	A	D	C	B	A	A	A	-	D	B	B	D	B	C	A
Acetamide	-	B	A	-	-	-	-	-	-	-	C	-	-	-	-	-	B	-	-	-	-	-	-	A	-	A	A	-	A	A	D	A
Acetate Solv. ²	A	B	A	B	B	-	-	A	C	B	A	-	B	D	A	-	-	A	-	B	D	-	A	A	-	D	D	-	D	-	-	A
Acetic Acid, Glacia ¹	-	B	A	A	B	A	A	C	C	D	A	-	C	B	A	C	D	D	D	B	B	A	A	A	-	D	D	B	C	B	C	B
Acetic Acid 20%	-	B	A	-	-	A	A	-	C	-	-	A	B	-	A	A	-	D	-	-	A	A	-	A	-	A	C	-	C	-	-	B
Acetic Acid 80%	-	B	A	-	-	A	A	-	C	-	-	A	D	-	A	B	-	D	-	-	B	-	-	A	-	A	C	-	D	-	-	B
Acetic Acid	-	B	A	B	B	A	A	C	C	D	C	B	A	B	A	A	D	D	C	B	A	A	A	A	-	C	C	-	C	B	C	A
Acetic Anhydride	B	A	A	B	B	A	A	C	D	B	D	D	D	D	A	D	D	D	D	A	A	A	A	A	-	D	A	C	B	B	C	A
Acetone ⁶	A	A	A	B	A	A	A	A	A	A	A	D	D	D	A	D	B	A	D	C	B	A	A	A	A	D	D	B	C	A	D	B
Acetyl Chloride	-	C	A	-	-	-	-	D	-	-	-	-	-	-	A	-	-	-	-	-	-	-	A	-	-	A	-	-	-	-	A	A
Acetylene ²	A	A	A	A	A	B	-	B	-	A	A	-	B	-	-	-	A	A	-	-	D	A	A	A	-	A	A	C	B	A	C	A
Acrylonitrile	A	A	C	-	B	B	B	A	-	C	-	-	-	-	-	-	B	-	D	-	B	A	A	A	-	C	D	-	D	D	-	A
Alcohols																																
Amyl	A	A	A	-	C	A	A	A	B	C	C	A	A	B	A	C	A	A	B	B	B	A	A	A	-	A	A	D	A	A	C	A
Benzyl	-	A	A	-	B	A	A	A	C	-	-	-	D	B	-	A	A	A	D	D	A	-	A	A	-	A	D	-	B	B	D	A
Butyl	A	A	A	-	B	B	A	B	C	C	C	A	A	B	A	A	A	A	-	B	B	A	A	A	-	A	A	D	A	A	A	A
Diacetone ²	-	A	A	-	A	A	A	A	C	-	A	-	D	-	-	A	A	A	-	-	D	-	A	A	-	D	D	-	D	A	D	A
Ethyl	-	A	A	A	B	A	A	A	C	A	A	-	A	C	-	A	B	A	B	B	A	-	A	A	A	A	A	B	A	B	A	A
Hexyl	-	A	A	-	A	A	A	A	C	-	A	-	-	-	-	A	A	A	-	-	A	-	A	A	-	A	A	D	B	A	A	A
Isobutyl	-	A	A	-	B	A	A	A	C	-	A	-	-	-	-	A	A	A	B	-	A	-	A	A	-	A	C	B	A	A	A	A
Isopropyl	-	A	A	-	B	A	A	A	C	C	A	-	-	-	-	A	A	A	-	-	A	-	A	A	-	A	C	C	B	A	A	A
Methyl ⁶	-	A	A	A	B	A	A	A	C	A	A	-	B	-	A	A	C	A	D	B	A	-	A	A	A	C	B	-	A	A	A	A
Octyl	-	A	A	-	A	A	A	A	C	-	A	-	-	-	-	A	A	A	-	-	-	-	A	A	-	A	B	-	B	A	C	A
Propyl	-	A	A	-	A	A	A	A	-	-	A	B	A	-	A	A	A	A	-	-	A	-	A	A	-	A	A	B	A	A	A	A

Chemical Resistance Chart

Aluminum Chloride - Beer

RATINGS - CHEMICAL EFFECT
A: No effect - Excellent
B: Minor effect - Good
C: Moderate effect - Fair
D: Severe effect - Not Recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cycloc (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy			
Aluminum Chloride 20%	-	D	C	D	B	A	A	D	-	D	A	-	A	B	-	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	A	A			
Aluminum Chloride	C	D	C	-	D	C	A	C	-	D	B	A	A	A	A	-	D	-	-	A	A	A	A	A	-	A	A	C	A	-	-	A			
Aluminum Fluoride	-	D	C	D	-	D	B	-	-	-	A	A	A	-	A	A	C	D	-	B	A	-	A	-	-	A	A	C	A	-	C	A			
Aluminum Hydroxide ⁶	-	A	A	A	A	-	-	A	-	D	A	-	A	-	A	A	B	A	-	-	A	-	A	A	A	A	A	-	A	-	A	A			
Alum Potassium Sulfate (Alum), 10%	-	A	-	-	A	-	B	-	-	D	A	-	A	-	A	-	-	A	-	A	-	-	A	A	-	A	-	-	A	-	A	A			
Alum Potassium Sulfate (Alum), 100%	-	D	A	B	B	-	B	C	-	-	A	-	A	B	A	A	C	D	-	B	A	-	A	A	-	A	A	-	A	-	A	A			
Aluminum Sulfate	-	C	C	A	A	A	A	C	C	D	A	A	A	B	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	A	A			
Amines	A	A	A	-	A	B	A	B	-	A	B	-	C	A	A	B	D	A	-	-	-	-	-	A	A	-	D	D	C	B	B	C	A		
Ammonia 10%	-	-	A	-	-	A	A	-	-	-	-	D	A	-	A	A	-	A	-	-	A	A	-	A	-	A	D	-	A	-	-	B			
Ammonia, Anhydrous	A	B	A	A	B	B	A	D	-	D	B	D	A	B	A	A	D	A	-	B	A	B	C	A	-	D	B	B	A	A	D	A			
Ammonia, Liquids	-	A	A	A	D	-	B	D	-	A	A	-	A	B	A	A	D	-	-	D	A	-	A	A	-	D	B	B	A	A	D	A			
Ammonia, Nitrate	-	A	A	A	C	-	-	D	-	-	A	-	B	B	-	A	C	-	-	-	A	-	A	A	-	-	A	-	C	-	-	A			
Ammonium Bifluoride	-	C	A	-	D	-	B	-	-	-	-	-	A	-	-	A	D	-	-	-	A	-	-	A	-	A	A	-	A	-	-	A			
Ammonium Carbonate	B	A	A	A	C	A	B	B	-	C	B	-	A	B	A	A	D	A	-	-	A	-	A	A	-	B	D	C	A	A	-	A			
Ammonium Casenite	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	A	D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	A
Ammonium Chloride	C	A	C	A	C	D	A	D	C	D	D	A	A	B	A	A	B	A	-	B	A	A	A	A	-	A	A	C	A	A	A	A	A		
Ammonium Hydroxide	A	A	A	A	C	A	A	D	D	A	C	-	A	B	A	A	D	A	B	B	A	A	A	A	-	B	B	B	A	A	C	A	A		
Ammonium Nitrate	A	A	A	A	B	A	A	D	D	A	D	-	A	B	A	A	C	D	-	B	A	A	A	A	-	D	A	C	A	A	A	A	A		
Ammonium Oxalate	-	A	A	A	-	-	A	-	-	-	A	-	-	-	-	-	B	-	-	-	-	-	-	A	-	-	-	A	-	A	-	-	A		
Ammonium Persulfate	-	A	A	A	C	C	A	A	-	D	A	D	A	-	A	A	D	D	-	-	A	-	A	A	-	C	A	-	A	A	A	A	A		
Ammonium Phosphate, Dibasic	B	A	A	A	B	A	A	C	-	-	D	-	A	-	A	A	B	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	A		
Ammonium Phosphate, Monobasic	-	A	A	A	B	A	A	D	-	-	A	-	A	A	A	A	B	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	A		
Ammonium Phosphate, Tribasic	B	A	A	A	B	A	A	C	-	C	D	-	A	-	A	A	B	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	A		
Ammonium Sulfate	C	D	B	A	B	A	A	B	C	C	C	A	A	D	A	A	B	D	-	B	A	A	A	A	-	D	A	B	A	A	A	A	A		
Ammonium Thio-Sulfate	-	-	A	-	-	A	-	-	-	D	A	-	-	-	-	-	B	-	-	-	-	-	-	A	A	-	-	A	-	-	-	-	A		
Amyl-Acetate	B	A	A	C	B	A	A	C	-	-	C	C	D	D	A	D	A	B	-	D	D	A	A	A	-	D	D	D	D	A	D	A	A		
Amyl Alcohol	-	A	A	-	B	A	A	A	-	-	A	A	A	B	A	C	A	A	-	B	A	-	A	A	-	B	B	D	A	A	C	A	A		
Amyl Chloride	-	C	B	-	D	-	A	A	-	-	A	A	D	C	A	D	A	C	-	D	D	-	A	A	-	A	D	-	D	D	D	A	A		
Aniline	B	A	A	A	C	A	B	C	-	-	C	C	D	D	A	D	D	C	D	C	B	A	A	A	-	C	D	C	D	B	D	A	A		
Anti-Freeze	-	A	A	-	A	-	A	B	B	B	C	-	A	B	A	A	A	A	B	B	A	A	A	A	A	A	A	A	C	A	A	A	A	A	
Antimony Trichloride	-	D	D	-	D	C	A	-	-	-	-	-	A	A	A	-	-	D	-	A	-	-	-	A	-	A	-	-	C	-	-	A	A		
Aqua Regia (80%, HCl, 20%, HNO)	-	D	D	-	D	A	D	D	-	-	-	C	D	D	A	D	D	D	-	D	C	-	-	D	-	C	D	C	D	D	D	D	D		
Arochlor 1248	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	D	-	-	-	-	-	-	-	A	-	-	A	D	-	D	B	D	A		
Aromatic Hydrocarbons	-	-	A	-	A	-	-	A	-	A	A	-	D	-	-	D	A	-	-	C	-	-	A	-	-	A	D	-	D	D	D	A	A		
Arsenic Acid	B	A	A	-	D	-	-	D	B	D	D	A	A	B	A	A	D	A	-	B	A	-	A	A	-	A	A	-	A	-	C	A	A		
Asphalt	-	B	A	-	C	-	-	A	-	C	-	-	A	-	-	-	A	A	-	-	A	A	-	A	A	-	A	B	C	B	D	D	A		
Barium Carbonate	B	A	A	A	B	A	A	B	-	B	B	-	A	A	A	A	A	A	-	B	A	-	A	A	A	A	A	-	A	-	A	A	A	A	
Barium Chloride	C	D	A	A	D	A	A	B	-	-	C	A	A	B	A	A	A	B	-	B	A	A	A	A	-	A	A	B	A	A	A	A	A		
Barium Cyanide	-	-	A	-	-	-	-	C	-	-	A	-	-	-	-	-	B	-	-	B	-	-	A	-	-	A	C	-	A	A	-	-	A		
Barium Hydroxide	B	C	A	A	D	B	B	B	-	C	C	A	A	-	A	A	D	A	-	B	A	A	A	A	A	A	A	C	A	A	A	A	A		
Barium Nitrate	-	A	A	-	-	A	-	D	-	A	A	-	B	-	-	A	A	-	-	-	-	-	-	A	A	-	A	A	-	A	A	-	-	B	
Barium Sulfate	B	A	A	A	D	A	A	C	-	C	C	A	A	-	A	A	A	A	-	B	A	A	A	B	-	A	A	D	A	A	-	-	B		

FOOTNOTES

- 1. P.V.C. - Satisfactory to 72° F.
- 2. Polypropylene - Satisfactory to 72° F.
- 3. Polypropylene - Satisfactory to 120° F.
- 4. Buna-N - Satisfactory for "O" Rings
- 5. Polyacetal - Satisfactory to 72° F.
- 6. Ceramag - Satisfactory to 72° F.

Chemical Resistance Chart

Beet Sugar Liquids - Chlorobenzene

RATINGS - CHEMICAL EFFECT
A: No effect - Excellent
B: Minor effect - Good
C: Moderate effect - Fair
D: Severe effect - Not Recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy		
Beet Sugar Liquids	A	A	A	-	A	-	-	A	B	A	-	-	A	-	A	A	B	A	B	-	A	-	A	A	-	A	A	-	B	A	A	A		
Benzaldehyde ³	A	A	A	-	B	A	A	A	-	B	A	C	D	D	A	D	A	C	D	D	D	A	A	A	-	D	D	B	D	A	D	A		
Benzene ²	B	A	A	A	B	A	B	B	A	B	C	B	D	C	A	D	A	A	D	D	D	A	A	A	A	A	D	-	D	D	D	A		
Benzoic Acid ²	B	A	A	A	B	A	A	B	-	D	-	A	A	B	A	A	B	D	-	B	D	-	A	B	-	A	D	-	D	D	D	A		
Benzol	-	A	A	-	B	A	A	B	A	-	-	-	D	-	A	D	A	A	-	-	A	-	A	A	A	D	D	-	D	-	-	A		
Borax (Sodium Borate)	-	A	A	A	C	B	A	A	B	A	C	A	A	A	A	A	A	A	-	B	A	A	A	A	A	A	B	C	A	A	C	A		
Boric Acid	B	A	A	A	B	A	A	B	C	D	-	A	A	B	A	A	A	A	-	B	A	-	A	A	A	A	A	-	A	A	A	A		
Brewery Slop	-	-	A	-	-	-	-	A	-	A	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	A	A	-	A	-	-	A		
Bromine ² (wet)	D	D	D	D	D	A	A	C	-	D	D	A	B	B	A	D	D	D	D	D	D	D	D	A	D	A	D	D	D	D	D	C		
Butadiene	A	A	A	-	A	-	-	C	A	C	C	A	A	-	A	-	A	A	-	-	-	B	A	A	-	A	A	-	B	A	-	A		
Butane ^{2 1}	A	A	A	-	A	-	-	A	A	C	C	A	A	C	A	D	A	A	B	C	D	A	A	A	-	A	A	D	B	D	D	A		
Butanol	-	A	A	-	A	-	A	A	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Butter	-	B	A	-	A	-	-	D	-	D	-	-	-	B	-	B	A	-	B	-	-	-	A	A	-	A	A	-	B	A	D	A		
Buttermilk	A	A	A	A	A	-	-	D	-	D	-	-	-	B	A	A	A	A	B	-	-	-	A	A	-	A	A	-	A	-	D	A		
Butylene	A	B	A	-	A	-	-	A	A	A	A	-	B	-	A	-	A	-	-	-	-	A	A	A	-	A	B	-	-	D	D	A		
Butyl Acetate ¹	-	-	C	-	A	-	A	A	-	-	A	C	D	D	A	D	A	-	-	C	D	A	A	A	-	D	B	D	D	B	D	A		
Butyric Acid ¹	B	B	A	A	B	A	A	C	-	D	-	A	B	-	A	A	C	D	D	-	A	-	A	D	-	D	D	-	D	B	-	A		
Calcium Bisulfate	C	D	A	-	D	-	-	D	D	D	-	-	A	A	A	-	-	A	-	-	-	-	-	-	-	-	A	A	C	C	-	A	A	
Calcium Bisulfide	-	-	B	-	C	A	A	C	-	-	-	-	A	-	A	A	D	A	-	B	A	-	A	A	-	A	A	-	A	D	-	A	A	
Calcium Bisulfite	-	B	A	-	C	A	A	C	-	-	-	A	A	-	A	A	-	A	-	-	A	-	-	A	-	A	A	-	A	-	A	-		
Calcium Carbonate	B	A	A	A	C	A	A	C	-	D	-	-	A	A	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	-	A	A	A	
Calcium Chlorate	-	B	A	-	-	B	B	C	-	-	-	-	A	A	A	-	-	A	-	A	-	-	A	-	-	A	-	-	A	-	A	A	A	
Calcium Chloride	C	A	D	C	C	A	A	B	-	C	-	A	A	A	A	A	D	A	B	B	A	A	A	A	B	A	A	B	D	A	A	A	A	
Calcium Hydroxide	B	A	A	-	C	A	A	B	-	-	-	-	A	A	A	A	B	A	-	B	A	-	A	A	A	A	A	C	A	A	A	A	A	
Calcium Hypochlorite	D	D	C	C	C	A	B	D	-	D	-	A	D	-	A	A	D	D	-	B	A	-	A	A	-	A	B	C	D	A	C	A	A	
Calcium Sulfate	B	A	A	A	B	A	B	B	-	-	-	A	A	A	A	A	A	A	C	B	A	A	A	A	-	A	A	-	D	-	C	A	A	
Calgon	-	A	A	-	-	-	-	C	-	D	-	-	-	-	-	A	B	-	-	-	A	-	A	A	-	A	A	-	A	-	-	A	A	
Cane Juice ²	-	A	A	-	B	-	-	B	C	A	-	-	A	-	-	-	A	A	-	-	D	-	A	A	-	-	A	-	A	-	A	A	A	
Carbolic Acid (See Phenol)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Carbon Bisulfide ²	B	A	A	A	A	-	-	C	-	B	-	-	D	D	-	-	A	A	-	-	D	-	A	A	A	A	D	-	D	D	D	A	A	
Carbon Dioxide (wet)	-	A	A	-	C	-	A	C	C	C	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Carbon Disulfide ²	-	B	A	-	C	-	-	C	C	B	C	-	D	C	A	D	A	A	-	D	D	A	A	B	-	A	D	-	D	D	D	A	A	
Carbon Monoxide	-	A	A	-	A	-	-	-	-	-	-	-	A	-	-	B	A	A	-	B	A	-	A	A	-	A	A	B	B	A	C	A	A	
Carbon Tetrachloride ^{2 1}	B	B	B	A	C	A	A	C	A	C	D	A	C	C	A	D	A	A	D	D	D	C	A	A	A	A	C	C	D	-	D	C	A	
Carbonated Water	B	A	A	A	A	-	-	B	-	D	-	-	A	-	-	A	A	A	-	-	A	-	A	A	-	A	A	-	A	A	-	A	A	A
Carbonic Acid	B	A	B	A	A	-	A	B	-	D	-	A	A	-	A	A	A	A	-	B	A	-	A	A	-	A	B	B	A	A	A	A	A	
Catsup	-	A	A	A	D	-	-	C	-	D	-	-	A	-	-	A	B	A	B	-	A	-	A	A	-	A	A	-	C	-	-	A	A	
Chloroacetic Acid ²	D	D	D	D	C	A	A	D	-	D	-	D	A	D	A	-	D	D	-	D	D	-	A	A	-	D	D	-	D	B	D	B	B	
Chloric Acid	-	D	D	-	-	-	-	-	-	-	-	-	D	-	A	-	-	-	-	-	-	-	-	-	-	-	-	D	-	D	-	-	D	
Chlorinated Glue	-	A	A	-	D	-	-	C	-	D	-	-	-	-	C	-	C	D	-	-	-	-	-	A	-	A	C	-	D	B	D	A	A	
Chlorine, Anhydrous Liquid	-	D	D	D	D	D	A	D	-	C	-	-	D	B	A	A	D	D	-	D	D	C	A	D	-	A	D	-	D	B	D	B	B	
Chlorine (dry)	B	A	A	-	D	D	A	A	B	A	-	-	-	A	-	-	-	-	-	-	-	-	C	A	A	-	D	-	-	D	-	D	D	
Chlorine Water	D	-	D	-	D	A	B	D	D	D	-	A	A	-	A	C	-	D	-	-	D	C	C	A	-	A	D	C	D	-	-	-	-	
Chlorobenzene (Mono)	A	A	A	-	B	-	A	B	-	B	C	A	D	D	A	D	A	A	D	D	D	A	A	A	-	A	D	-	D	D	D	A	A	

FOOTNOTES

- 1. P.V.C. - Satisfactory to 72° F.
- 2. Polypropylene - Satisfactory to 72° F.
- 3. Polypropylene - Satisfactory to 120° F.
- 4. Buna-N - Satisfactory for "O" Rings
- 5. Polyacetal - Satisfactory to 72° F.
- 6. Ceramag - Satisfactory to 72° F.

Chemical Resistance Chart

Chloroform - Ferrous Chloride

RATINGS - CHEMICAL EFFECT
A: No effect - Excellent
B: Minor effect - Good
C: Moderate effect - Fair
D: Severe effect - Not Recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cyclocac (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy	
Chloroform	A	A	A	A	D	A	A	B	-	D	C	C	D	C	A	D	A	C	D	D	D	C	A	A	A	A	D	D	D	D	D	A	
Chlorosulfonic Acid ¹	D	D	-	D	D	A	B	D	-	-	D	D	C	C	A	D	D	D	-	D	D	D	-	C	-	D	D	D	D	D	D	D	C
Chlorox (Bleach)	-	A	A	-	C	-	A	A	-	D	C	-	A	B	A	A	D	D	B	-	D	C	A	A	-	A	C	-	B	B	D	A	
Chocolate Syrup	-	A	A	-	A	-	-	-	-	D	-	-	-	-	A	A	A	A	-	-	A	-	-	A	-	A	A	-	A	-	D	A	
Chromic Acid 5%	-	A	A	B	C	A	A	D	D	D	-	-	A	B	-	C	D	D	B	B	A	A	D	C	-	A	D	C	D	A	B	B	
Chromic Acid 10%	-	B	-	-	-	A	A	-	D	-	-	A	A	-	A	A	-	D	-	-	A	-	-	A	-	A	D	-	D	-	-	C	
Chromic Acid 30%	-	B	-	-	-	A	A	-	D	-	-	B	A	-	A	D	-	D	-	-	A	-	-	A	-	A	D	-	D	-	-	D	
Chromic Acid 50%	C	B	B	-	C	A	A	D	D	D	-	C	B	B	A	D	D	D	C	C	B	B	D	A	-	A	D	-	D	A	D	C	
Cider	-	A	A	A	B	-	-	A	-	D	-	-	A	-	-	A	B	-	-	B	-	-	A	A	-	A	A	-	A	-	-	A	
Citric Acid	-	A	A	A	C	A	A	D	C	D	-	A	A	-	A	A	B	C	C	B	B	-	A	A	B	A	D	C	A	A	A	A	
Citric Oils	-	A	A	-	C	-	-	B	-	-	-	-	-	-	-	A	B	-	-	-	A	-	A	A	-	A	A	C	D	-	-	A	
Coffee	A	A	A	A	A	-	-	B	-	C	-	-	-	-	A	A	A	A	-	-	A	-	A	A	-	A	A	-	A	-	A	A	
Copper Chloride	C	D	D	B	D	A	A	D	-	D	-	A	A	B	A	A	B	D	-	B	A	A	-	A	-	A	A	-	A	A	A	A	
Copper Cyanide	-	A	A	A	D	A	A	C	-	D	-	A	A	-	A	A	B	A	-	B	A	A	A	A	-	B	B	-	A	A	A	C	
Copper Florobate	-	D	D	-	D	-	B	D	-	D	-	-	A	A	-	B	-	-	A	-	-	A	-	-	A	B	-	A	-	A	A		
Copper Nitrate	B	A	A	B	D	A	A	D	-	-	-	A	A	-	A	A	B	D	-	B	A	-	A	A	-	A	A	-	A	-	-	A	
Copper Sulfate (5% Sol)	-	A	A	A	D	A	A	D	D	D	-	-	A	-	A	A	B	D	-	B	A	A	A	A	-	A	A	C	A	-	C	A	
Copper Sulfate	B	B	-	-	-	A	A	C	D	-	-	A	A	-	A	A	-	C	-	-	A	-	-	A	-	B	B	-	A	A	-	A	
Cream	-	A	A	-	A	-	-	C	-	D	-	-	-	-	-	A	A	A	-	-	A	-	A	A	-	A	A	-	C	-	-	A	
Cresols ²	-	A	A	-	B	-	-	D	C	-	-	-	D	D	-	D	-	D	D	C	A	A	A	-	D	D	D	D	D	D	D	A	
Cresylic Acid	B	A	A	-	C	A	B	C	-	-	-	B	B	D	A	-	D	D	-	C	-	-	A	A	-	A	D	-	D	D	D	A	
Cyclohexane	-	A	-	-	A	A	-	A	-	-	A	-	-	D	-	D	A	-	-	-	D	A	A	A	-	A	A	D	D	D	D	A	
Cyanic Acid	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	D	-	-	-	-	-	-	-	-	-	-	C	-	D	-	-	A	
Detergents	-	A	A	-	A	-	-	A	-	-	A	-	A	-	-	A	B	A	B	B	A	A	A	A	-	A	A	-	B	A	C	A	
Dichlorethane	-	A	A	-	-	-	A	-	-	-	-	-	D	D	A	-	-	A	-	D	-	-	-	-	-	B	-	-	D	-	D	A	
Diesel Fuel	A	A	A	-	A	-	-	A	-	A	A	-	-	-	-	D	A	-	-	-	D	A	A	A	-	A	A	-	D	D	D	A	
Diethylamine	A	A	-	-	A	-	-	A	-	-	-	-	D	-	A	B	D	-	-	-	C	-	A	A	-	D	B	-	B	B	C	A	
Diethylene Glycol	-	A	-	-	-	-	-	A	-	-	-	-	-	-	-	A	A	A	B	B	-	-	A	A	-	A	A	C	A	A	A	A	
Diphenyl Oxide	-	A	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	A	D	-	D	D	D	A	
Dyes	-	A	A	-	B	-	-	C	-	-	-	-	-	-	-	A	A	-	-	-	-	-	-	-	-	A	-	-	C	-	-	A	
Epsom Salts (Magnesium Sulfate)	B	A	A	A	A	A	B	B	-	-	-	-	A	-	-	A	A	-	-	-	A	-	A	A	-	A	A	-	A	-	C	A	
Ethane	A	A	-	-	A	-	-	A	-	-	-	-	-	-	-	D	A	-	-	-	-	-	A	A	-	A	A	-	B	D	D	A	
Ethanolamine	-	A	A	-	-	-	-	-	-	C	-	-	-	-	-	D	-	-	-	-	-	A	A	A	-	D	B	C	B	-	C	A	
Ether ³	A	A	A	A	A	-	B	B	A	-	B	-	D	C	-	D	A	C	-	-	-	A	A	A	A	C	D	-	D	C	D	A	
Ethyl Acetate ²	-	A	A	-	B	-	B	B	-	-	C	D	D	D	A	D	A	A	D	C	C	A	A	A	-	D	D	C	D	B	D	A	
Ethyl Chloride	-	A	A	A	B	A	B	B	-	C	D	A	D	D	A	D	A	A	-	D	D	A	A	A	-	A	D	D	C	A	A	A	
Ethyl Sulfate	-	D	-	-	-	-	-	-	-	-	-	-	-	-	-	B	-	-	-	-	-	-	A	A	-	A	A	-	-	-	-	A	
Ethylene Chloride ²	-	A	A	-	C	B	B	A	-	C	C	-	D	-	A	D	A	-	D	-	D	A	A	A	-	A	D	D	D	C	D	A	
Ethylene Dichloride	-	A	A	-	D	A	B	C	-	-	C	-	D	D	A	D	A	A	-	D	A	A	C	A	-	A	D	D	D	C	D	A	
Ethylene Glycol ⁴	-	A	A	-	A	-	A	B	B	B	C	A	A	B	A	A	A	A	B	B	A	A	A	A	A	A	A	C	A	A	A	A	
Ethylene Oxide	-	-	A	-	A	-	-	A	-	-	-	-	D	-	A	A	A	A	-	-	-	-	-	A	A	-	D	D	D	D	C	D	A
Fatty Acids	-	A	A	-	B	A	A	C	-	D	-	A	A	B	A	B	A	A	-	B	A	-	A	A	-	A	C	C	B	C	C	A	
Ferric Acid	-	D	D	D	D	A	B	D	D	D	-	A	A	B	A	A	B	D	-	B	A	A	A	A	-	A	D	C	B	A	A	A	
Ferric Nitrate	-	A	A	A	D	A	A	D	-	-	-	A	A	-	A	A	B	D	-	B	A	A	A	A	-	A	A	D	A	A	A	A	
Ferric Sulfate	-	A	C	A	D	A	A	D	D	D	-	A	A	B	A	A	B	A	C	-	A	A	C	A	-	A	B	C	A	-	A	A	
Ferrous Chloride	-	D	D	-	D	A	B	C	-	D	-	A	A	B	A	A	B	D	-	B	A	A	A	A	-	A	B	C	A	-	A	A	

FOOTNOTES
 1. P.V.C. - Satisfactory to 72° F. 3. Polypropylene - Satisfactory to 120° F. 5. Polyacetal - Satisfactory to 72° F.
 2. Polypropylene - Satisfactory to 72° F. 4. Buna-N - Satisfactory for "O" Rings 6. Ceramag - Satisfactory to 72° F.

Chemical Resistance Chart

Hydrogen Gas - Methyl Acrylate

RATINGS - CHEMICAL EFFECT
A: No effect - Excellent
B: Minor effect - Good
C: Moderate effect - Fair
D: Severe effect - Not Recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy	
Hydrogen Gas	A	A	A	-	A	-	-	A	-	B	B	A	A	-	A	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	
Hydrogen Peroxide 10%	-	C	C	-	A	C	A	D	D	D	-	-	A	A	A	-	-	D	-	A	-	B	A	A	-	-	A	-	-	-	-	-	D
Hydrogen Peroxide 30%	-	-	B	-	-	B	A	-	D	-	-	-	A	-	A	-	-	D	-	-	A	C	-	-	-	A	D	-	-	-	-	-	B
Hydrogen Peroxide	-	A	B	A	A	B	A	D	D	D	D	C	A	C	A	B	D	D	-	B	A	C	-	A	A	A	D	C	D	C	C	A	
Hydrogen Sulfide, Aqueous Solution	-	D	A	C	C	A	A	D	C	D	-	A	A	B	A	A	D	D	-	B	A	A	A	A	A	D	C	-	B	A	D	A	
Hydrogen Sulfide (dry)	A	C	A	-	D	-	A	D	C	B	B	-	A	-	A	-	-	D	-	-	-	A	-	A	-	D	-	-	-	-	-	A	A
Hydroxyacetic Acid (70%)	-	-	-	-	D	B	-	-	-	-	-	-	A	-	-	-	D	-	-	-	-	-	A	A	-	A	A	-	A	A	-	A	A
Ink	A	A	A	-	C	-	-	C	-	D	D	-	-	-	-	B	A	A	-	B	-	-	A	A	A	A	A	A	-	A	-	-	A
Iodine	-	D	D	D	D	A	B	D	-	D	-	-	D	B	A	A	C	D	D	D	D	-	D	A	-	A	B	-	D	B	D	A	
Iodine (in Alcohol)	-	-	B	-	-	D	A	-	-	-	-	-	D	-	A	C	-	D	-	-	B	-	-	A	-	A	D	-	D	-	-	-	
Iodoform	B	C	A	-	A	-	-	C	-	C	B	-	-	-	A	-	-	A	-	-	-	-	-	-	-	A	-	-	-	-	-	-	
Isotane ²	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	D	A	-	-	-	D	-	-	A	-	A	A	-	-	-	-	D	A
Isopropyl Acetate	-	-	B	-	C	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	D	D	-	D	B	D	A	
Isopropyl Ether ²	A	-	A	-	A	-	-	A	-	-	A	-	-	-	A	D	A	-	-	-	D	-	A	A	-	D	B	-	D	D	D	-	
Jet Fuel (JP#, JP4, JP5)	A	A	A	-	A	-	-	A	-	A	A	A	A	-	A	D	A	A	-	-	D	A	A	A	-	A	A	D	D	D	D	A	
Kerosene ²	A	A	A	A	A	A	A	A	A	B	A	A	D	A	D	A	A	B	D	D	A	A	A	A	A	A	D	D	A	D	A	A	
Ketones	A	A	A	-	B	A	A	A	-	A	A	D	D	D	A	D	B	A	-	D	D	A	C	A	-	D	D	-	D	D	C	C	
Lacquers	A	A	A	-	A	-	-	A	C	C	C	-	-	D	-	C	A	A	-	-	A	-	A	A	-	D	D	-	D	-	D	A	
Lacquer Thinners	-	-	A	-	-	A	A	-	C	-	-	-	C	-	A	D	-	A	-	-	B	-	-	A	-	-	D	-	D	A	-	-	
Lactic Acid	A	A	B	C	C	A	A	D	-	D	D	C	A	B	A	A	B	C	-	B	A	A	A	A	-	B	B	-	A	B	A	A	
Lard	B	A	A	A	A	-	-	A	-	A	C	-	A	-	-	-	A	A	C	-	A	-	A	A	-	A	A	C	B	-	D	A	
Latex	-	A	A	-	A	-	-	A	-	-	-	-	-	-	-	A	A	A	-	B	-	-	-	A	-	A	A	-	C	A	-	A	
Lead Acetate	B	A	A	-	D	A	A	C	-	-	D	-	A	B	A	A	A	A	-	B	A	-	A	A	-	D	B	-	D	A	A	A	
Lead Sulfamate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	A	-	-	-	-	A	B	C	A	D	C	A	
Ligroin ³	-	-	A	-	-	-	-	A	-	-	-	-	-	-	-	D	A	-	-	-	D	-	-	A	-	A	A	-	B	A	D	A	
Lime	-	A	A	-	C	A	-	A	-	A	-	-	A	-	-	A	D	-	C	-	-	-	A	A	-	A	A	C	B	D	-	A	
Lubricants	-	A	A	-	A	A	A	B	-	-	-	-	A	-	-	A	A	-	-	B	A	-	-	A	-	A	A	C	D	-	D	A	
Magnesium Carbonate	-	A	A	A	-	-	B	-	-	-	-	-	A	-	-	A	A	-	-	B	A	-	-	A	-	A	-	A	A	-	A	A	
Magnesium Chloride	B	B	B	A	D	A	A	B	C	D	C	-	A	B	A	A	A	A	-	B	A	A	-	A	-	A	A	-	A	A	A	A	
Magnesium Hydroxide	A	A	A	-	D	A	A	C	B	B	B	A	A	-	A	A	A	A	-	B	A	A	A	A	-	A	B	-	B	-	C	A	
Magnesium Nitrate	-	A	A	A	-	A	A	-	-	-	-	-	A	-	A	A	A	A	-	B	A	-	-	A	-	A	A	-	A	-	-	A	
Magnesium Oxide	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	A	-	-	A	-	A	A	-	A
Magnesium Sulfate	B	B	A	-	B	A	B	B	B	C	B	-	A	B	A	A	A	A	-	B	A	A	A	A	-	A	A	-	A	D	C	A	
Maleic Acid	C	A	A	A	B	A	A	C	-	-	B	-	A	B	A	A	C	A	-	-	C	-	A	A	-	A	D	-	A	D	D	A	
Maleic Anhydride	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	C	-	-	-	-	-	A	A	-	A	D	-	D	-	D	A	
Malic Acid	B	A	A	-	C	-	A	D	-	-	D	-	A	-	A	-	-	A	-	-	-	-	-	A	-	B	-	-	A	-	A	-	
Mash	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	A	A	-	-	-	-	-	A	A	-	-	A	-	A	-	-	A	
Mayonnaise	A	A	A	-	D	-	-	D	-	D	D	-	-	-	A	A	A	A	B	-	A	-	A	A	-	A	A	-	-	-	-	A	
Melamine	-	D	D	-	-	-	-	D	-	-	-	-	-	-	-	-	D	-	-	-	-	-	A	A	-	-	C	-	-	-	-	A	
Mercuric Chloride (Dilute Solution)	D	D	D	D	D	A	B	D	D	D	D	-	A	A	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	A	A	A	
Mercuric Cyanide	A	A	A	-	D	A	-	D	-	-	D	-	A	-	A	A	A	-	-	B	A	-	A	A	-	-	A	-	-	-	-	A	
Mercury	A	A	A	A	C	C	A	D	D	A	A	-	A	-	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	A	A	A	
Methanol (See Alcohol Methyl)																																	
Methyl Acetate	A	-	A	-	A	-	A	A	-	-	B	-	-	-	A	-	A	-	D	-	-	-	A	A	-	D	D	D	B	B	D	-	
Methyl Acrylate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	D	D	-	B	B	D	A

FOOTNOTES

- 1. P.V.C. - Satisfactory to 72° F.
- 2. Polypropylene - Satisfactory to 72° F.
- 3. Polypropylene - Satisfactory to 120° F.
- 4. Buna-N - Satisfactory for "O" Rings
- 5. Polyacetal - Satisfactory to 72° F.
- 6. Ceramag - Satisfactory to 72° F.

Chemical Resistance Chart

Methyl Acetone - Oils

RATINGS - CHEMICAL EFFECT
A: No effect - Excellent
B: Minor effect - Good
C: Moderate effect - Fair
D: Severe effect - Not Recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy	
Methyl Acetone	A	-	A	-	A	-	-	A	-	A	A	-	-	-	A	D	A	-	-	-	-	-	-	A	-	D	D	-	D	-	-	C	
Methyl Alcohol 10%	A	-	A	-	C	-	A	C	-	-	B	-	A	-	A	-	-	A	-	-	-	-	-	-	-	-	B	-	-	-	A	A	
Methyl Bromide	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	D	-	-	A	A	-	A	B	-	D	D	D	B	
Methyl Butyl Ketone	-	-	A	-	A	-	-	-	-	-	-	-	-	-	-	D	B	-	-	-	-	-	-	A	A	-	D	D	C	D	A	D	B
Methyl Cellosolve	-	-	-	-	A	-	-	A	-	-	-	-	-	-	-	C	B	-	-	-	A	-	A	A	-	D	D	-	D	B	D	C	
Methyl Chloride	-	A	A	-	D	A	A	A	-	-	-	A	D	-	A	D	A	A	-	D	D	-	A	A	-	A	D	D	D	C	D	A	
Methyl Dichloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	D	A	-	-	-	-	-	-	A	A	-	A	D	-	D	D	A	
Methyl Ethyl Ketone	-	A	A	-	A	A	A	A	-	-	-	D	D	-	A	D	B	A	D	D	A	A	A	A	-	D	D	C	D	A	D	B	
Methyl Isobutyl Ketone ²	-	-	A	-	-	A	A	-	-	-	-	D	D	-	A	D	B	A	D	-	C	A	A	A	-	D	D	C	D	C	D	B	
Methyl Isopropyl Ketone	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	D	B	A	-	-	-	-	-	A	A	-	D	D	B	D	B	B	
Methyl Methacrylate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	D	D	-	D	D	A	
Methylamine	A	-	A	-	A	-	-	D	-	B	B	-	-	-	-	B	D	-	-	-	-	-	-	A	A	-	-	B	-	-	-	A	
Methylene Chloride	A	A	A	-	A	A	A	A	C	-	B	D	D	-	A	D	A	D	-	D	D	-	A	A	-	D	D	-	D	D	D	A	
Milk	A	A	A	A	A	-	-	C	C	D	D	-	A	-	-	A	A	A	B	B	A	-	A	A	A	A	A	A	B	A	A	A	A
Molasses	A	A	A	A	A	-	-	A	B	A	A	-	A	-	-	B	A	A	-	B	A	-	A	A	A	A	A	A	-	A	-	-	A
Mustard	A	A	A	A	B	-	-	B	-	C	B	-	A	-	-	B	B	A	B	-	A	-	A	A	-	A	B	C	C	-	-	A	
Naptha	A	A	A	A	A	A	A	B	-	B	B	A	A	C	A	D	A	A	C	D	A	A	A	A	-	A	B	D	D	D	D	A	
Napthalene	B	A	B	-	B	A	A	C	-	B	A	A	D	-	A	D	A	-	-	D	B	A	A	A	-	B	D	-	D	D	D	A	
Nickel Chloride	-	A	B	-	D	A	A	D	-	D	-	A	A	B	A	A	B	A	-	B	A	-	A	A	-	A	A	-	A	A	A	A	
Nickel Sulfate	B	A	B	-	D	A	B	C	C	D	D	A	A	A	A	A	B	A	-	B	A	-	A	A	-	A	A	-	A	A	C	A	
Nitric Acid (10% Solution)	A	A	A	A	D	A	A	D	-	D	D	A	A	B	A	A	D	D	C	B	A	D	C	B	D	A	D	-	D	B	D	A	
Nitric Acid (20% Solution)	-	A	A	A	D	A	A	D	-	D	-	B	A	B	A	A	D	D	D	B	A	C	D	C	D	A	D	-	D	D	D	B	
Nitric Acid (50% Solution)	-	A	A	A	D	A	A	D	-	D	-	B	A	B	A	A	D	D	D	C	D	C	D	A	-	A	D	-	D	D	D	D	
Nitric Acid (Concentrated Solution)	-	D	B	A	B	A	B	D	D	D	-	-	D	C	A	D	D	D	D	D	D	C	D	A	C	B	D	-	D	D	D	D	
Nitrobenzene ²	B	A	B	-	C	A	B	D	-	B	B	D	D	D	A	D	B	C	D	D	C	B	A	A	-	D	D	D	D	D	D	B	
Oils																																	
Aniline	-	A	A	-	C	A	D	A	-	A	-	-	D	-	A	D	D	C	D	-	A	-	A	A	-	A	D	-	D	B	D	A	
Anise	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	-	-	-	-	D	-	A
Bay	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	-	-	D	-	A	
Bone	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	A	-	D	-	A	
Castor	-	A	A	-	A	-	-	A	-	A	-	-	A	-	-	-	A	-	-	-	-	-	-	A	A	A	A	A	-	A	B	A	A
Cinnamon	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	-	A	-	-	-	-	A	A	-	D	-	-	D	-	-	A	
Citric	-	A	A	-	-	-	-	D	-	D	-	-	-	-	-	-	A	A	-	-	-	-	A	A	-	A	A	-	D	-	-	A	
Clove	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	-	B	-	A	A	-	-	A	-	-	-	-	A	
Coconut	-	A	A	-	B	-	-	A	-	A	-	-	-	-	-	-	A	A	-	-	-	-	-	A	A	-	A	A	-	A	A	D	A
Cod Liver	-	A	A	-	B	-	-	-	-	-	-	-	-	-	-	-	A	A	C	-	A	-	-	A	A	-	A	A	-	B	A	D	A
Corn	-	A	A	A	B	-	-	B	-	A	-	-	-	-	-	-	A	A	C	-	A	-	-	A	A	-	A	A	-	D	C	D	A
Cotton Seed	B	A	A	A	B	-	-	B	-	A	C	-	A	-	A	-	A	A	C	-	A	A	A	A	-	A	A	-	D	C	D	A	
Cresote ²	-	A	A	-	A	-	-	-	-	-	-	-	-	-	-	-	D	-	-	-	-	-	-	A	A	-	A	A	-	B	D	D	A
Diesel Fuel (2D, 3D, 4D, 5D)	-	A	A	-	A	-	-	A	-	-	-	-	-	-	-	-	D	A	A	-	-	-	-	A	A	-	A	A	-	D	D	D	A
Fuel (1,2,3,5A, 5B, 6)	-	A	A	-	A	A	A	A	-	-	-	-	A	-	A	D	A	-	-	-	-	-	B	-	A	A	-	A	B	-	D	D	A

FOOTNOTES

- 1. P.V.C. - Satisfactory to 72° F.
- 2. Polypropylene - Satisfactory to 72° F.
- 3. Polypropylene - Satisfactory to 120° F.
- 4. Buna-N - Satisfactory for "O" Rings
- 5. Polyacetal - Satisfactory to 72° F.
- 6. Ceramag - Satisfactory to 72° F.

Chemical Resistance Chart

Platings (Cont'd) - Zinc Plating

RATINGS - CHEMICAL EFFECT
A: No effect - Excellent
B: Minor effect - Good
C: Moderate effect - Fair
D: Severe effect - Not Recommended

302 Stainless Steel
 304 Stainless Steel
 316 Stainless Steel
 440 Stainless Steel
 Aluminum
 TITANIUM
 HASTELLOY C
 Cast Bronze
 Brass
 Cast Iron
 Carbon Steel
 KYNAR
 PVC (Type 1)
 Tygon (E-3606)
 Teflon
 Noryl
 Polyacetal
 Nylon
 Cycolac (ABS)
 Polyethylene
 POLYPROPYLENE
 RYTON
 CARBON
 CERAMIC
 CERAMAGNET "A"
 VITON
 BUNA N (NITRILE)
 Silicon
 Neoprene
 Ethylene Propylene (EPM)
 Rubber (Natural)
 Epoxy

Platings (Cont.)	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cycolac (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy
Copper-Zinc Bronze Bath 100°F	-	-	A	-	-	A	A	-	-	-	-	-	A	-	A	A	-	A	-	-	A	-	-	C	-	A	A	-	A	-	-	B
Cadmium Plating Cyanide Bath 90°F	-	-	A	-	-	A	A	-	-	-	-	-	A	-	A	A	-	A	-	-	A	-	-	C	-	A	A	-	A	-	-	B
Fluoborate Bath 100°F	-	-	A	-	-	D	A	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	D	-	A	B	-	C	-	-	B
Chromium Plating Chromic-Sulfuric Bath 130°F	-	-	C	-	-	A	A	-	-	-	-	-	A	-	A	D	-	D	-	-	A	-	-	A	-	C	D	-	D	-	-	D
Fluosilicate Bath 95°F	-	-	C	-	-	C	A	-	-	-	-	-	A	-	A	D	-	D	-	-	A	-	-	B	-	C	D	-	D	-	D	D
Fluoride Bath 130°F	-	-	D	-	-	C	A	-	-	-	-	-	A	-	A	D	-	D	-	-	A	-	-	B	-	C	D	-	D	-	-	D
Black Chrome Bath 115°F	-	-	C	-	-	A	A	-	-	-	-	-	A	-	A	D	-	D	-	-	A	-	-	A	-	C	D	-	D	-	-	D
Barrel Chrome Bath 95°F	-	-	D	-	-	C	A	-	-	-	-	-	A	-	A	D	-	D	-	-	A	-	-	A	-	C	D	-	D	-	-	D
Copper Plating (Cyanide) Copper Strike Bath 120°F				-	A	A	A	-	-	-	-	-		-	A	A	-		-	-		-	-	C	-	B	-	-	A	-	-	
Rochelle Salt Bath 150°F	-	-	A	-	-	A	A	-	-	-	-	-	D	-	A	A	-	A	-	-	A	-	-	D	-	A	A	-	B	-	-	C
High Speed Bath 180°F	-	-	A	-	-	A	A	-	-	-	-	-	D	-	A	A	-	A	-	-	A	-	-	D	-	A	A	-	B	-	-	C
Copper Plating (Acid) Copper Sulfate Bath R.T.	-	-	D	-	-	A	A	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	D	-	A	A	-	A	-	-	D
Copper Fluoborate Bath 120°F	-	-	D	-	-	D	A	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	D	-	A	B	-	C	-	-	D
Copper (Misc.) Copper Pyrophosphate 140°F	-	-	A	-	-	A	A	-	-	-	-	-	A	-	A	A	-	A	-	-	A	-	-	B	-	A	A	-	A	-	-	B
Copper (Electroless) 140°F	-	-	-	-	-	-	-	D	-	-	-	-	A	-	A	A	-	A	-	-	A	-	-	D	-	A	D	-	D	-	-	B
Gold Plating Cyanide 150°F	-	-	A	-	-	A	A	C	-	-	-	-	D	-	A	A	-	A	-	-	A	-	-	B	-	A	A	-	A	-	-	D
Neutral 75°F	-	-	C	-	-	A	A	-	-	-	-	-	A	-	A	A	-	A	-	-	A	-	-	A	-	A	A	-	A	-	-	A
Acid 75°F	-	-	C	-	-	A	A	-	-	-	-	-	A	-	A	A	-	A	-	-	A	-	-	A	-	A	A	-	A	-	-	A
Indium Sulfamate Plating R.T.	-	-	C	-	-	A	A	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	A	-	A	A	-	A	-	-	A
Iron Plating Ferrous Chloride Bath 190°F	-	-	D	-	-	A	D	-	-	-	-	-	D	-	A	A	-	D	-	-	C	-	-	A	-	A	B	-	D	-	-	D
Ferrous Sulfate Bath 150°F	-	-	C	-	-	A	A	-	-	-	-	-	D	-	A	A	-	D	-	-	A	-	-	A	-	A	A	-	B	-	-	D
Ferrous Am. Sulfate Bath 150°F	-	-	C	-	-	A	A	-	-	-	-	-	D	-	A	A	-	D	-	-	A	-	-	A	-	A	A	-	B	-	-	D
Sulfate-Chloride Bath 160°F	-	-	D	-	-	A	D	-	-	-	-	-	D	-	A	A	-	D	-	-	A	-	-	A	-	A	B	-	C	-	-	D
Fluoborate Bath 145°F	-	-	D	-	-	D	B	-	-	-	-	-	D	-	A	A	-	D	-	-	A	-	-	D	-	A	B	-	C	-	-	D
Sulfamate 140°F	-	-	D	-	-	A	B	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	A	-	A	A	-	A	-	-	A
Lead Fluoborate Plating	-	-	C	-	-	D	A	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	D	-	A	B	-	C	-	-	A
Nickel Plating Watts Type 115-160°F	-	-	C	-	-	A	A	-	-	-	-	-	D	-	A	A	-	A	-	-	A	-	-	A	-	A	A	-	A	-	-	D
High Chloride 130-160°F	-	-	C	-	-	A	A	-	-	-	-	-	D	-	A	A	-	D	-	-	A	-	-	A	-	A	A	-	B	-	-	D
Fluoborate 100-170°F	-	-	C	-	-	D	A	D	-	-	-	-	D	-	A	A	-	D	-	-	A	-	-	D	-	A	B	-	C	-	-	D
Sulfamate 100-140°F	-	-	C	-	-	A	A	-	-	-	-	-	A	-	A	A	-	A	-	-	A	-	-	A	-	A	A	-	A	-	-	A
Electroless 200°F	-	-	-	-	-	-	-	-	-	-	-	-	D	-	A	D	-	D	-	-	D	-	-	A	-	A	D	-	D	-	-	B
Rhodium Plating 120°F	-	-	D	-	-	D	D	-	-	-	-	-	A	-	A	A	D	D	-	-	A	-	-	A	-	A	A	-	B	-	-	A
Silver Plating 80-120°F	-	-	A	-	-	A	A	-	-	-	-	-	A	-	A	A	-	A	-	-	A	-	-	B	-	A	A	-	A	-	-	A
Tin-Fluoborate Plating 100°F	-	-	C	-	-	D	A	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	D	-	A	B	-	C	-	-	A
Tine-Lead Plating 100°F	-	-	C	-	-	D	A	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	D	-	A	B	-	C	-	-	A
Zinc Plating Acid Chloride 140°F	-	-	D	-	-	A	D	-	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	A	-	A	A	-	A	-	-	A
Acid Sulfate Bath 150°F	-	-	C	-	-	A	A	-	-	-	-	-	D	-	A	A	-	D	-	-	A	-	-	A	-	A	A	-	B	-	-	D

FOOTNOTES

1. P.V.C. - Satisfactory to 72° F.
2. Polypropylene - Satisfactory to 72° F.
3. Polypropylene - Satisfactory to 120° F.
4. Buna-N - Satisfactory for "O" Rings
5. Polyacetal - Satisfactory to 72° F.
6. Ceramag - Satisfactory to 72° F.

Chemical Resistance Chart

Sodium Hydroxide - Tartaric Acid

RATINGS - CHEMICAL EFFECT
A: No effect - Excellent
B: Minor effect - Good
C: Moderate effect - Fair
D: Severe effect - Not Recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cycloc (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy	
Sodium Hydroxide (20%)	-	A	A	A	D	A	A	C	D	A	-	A	A	B	A	A	D	C	C	B	A	A	C	D	A	A	A	D	B	A	A	A	
Sodium Hydroxide (50% Solution)	-	A	B	-	D	A	A	C	D	B	-	D	A	B	A	A	D	C	C	C	A	B	C	D	A	D	D	D	C	-	A	A	
Sodium Hydroxide (80% Solution)	-	A	D	-	D	A	B	C	D	C	-	-	A	B	A	A	D	C	C	C	A	B	C	D	A	B	D	D	C	-	B	A	
Sodium Hypochlorite (to 20%)	-	C	C	C	C	A	A	D	D	D	-	-	A	B	A	A	D	A	-	B	D	C	D	A	B	A	C	D	D	B	C	B	
Sodium Hypochlorite	D	-	A	-	D	A	A	D	-	D	D	A	A	-	A	A	-	A	-	-	A	C	-	D	-	B	B	C	A	-	-	A	
Sodium Hyposulfate	-	A	A	-	D	-	-	D	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	C	-	C	C
Sodium Metaphosphate ²	A	-	A	-	A	-	-	C	C	B	B	-	-	-	A	-	B	A	-	-	D	-	A	A	-	A	A	-	B	A	A	A	
Sodium Metasilicate	A	-	A	-	B	-	-	B	-	C	C	-	-	-	A	-	D	-	-	-	-	-	A	-	-	A	A	D	A	-	-	A	
Sodium Nitrate	B	A	A	A	A	A	B	B	C	A	B	A	A	B	A	A	B	A	-	B	A	-	A	A	A	D	C	D	B	A	C	A	
Sodium Perborate	B	-	C	-	B	-	-	C	C	B	B	-	-	-	A	A	B	A	-	-	A	-	A	A	-	A	B	D	B	A	C	A	
Sodium Peroxide	B	A	A	-	C	-	B	C	C	D	C	-	A	-	A	-	D	D	-	-	-	-	A	A	-	A	C	D	B	A	C	A	
Sodium Polyphosphate (Mono, Di, Tribasic)	-	A	A	-	D	A	A	C	-	-	-	-	-	-	A	A	B	-	-	-	-	-	A	A	-	A	A	-	D	A	A	A	
Sodium Silicate	B	A	B	A	C	A	B	C	C	-	B	-	A	B	A	A	C	A	-	-	A	-	A	A	-	A	A	-	A	A	A	A	
Sodium Sulfate	B	A	A	C	B	A	B	B	B	A	B	-	A	-	A	A	B	A	-	B	A	A	A	A	-	A	A	-	A	A	C	A	
Sodium Sulfide	B	A	B	-	D	A	B	D	D	A	B	-	A	B	A	A	B	A	-	B	A	A	A	A	-	A	C	-	A	A	C	A	
Sodium Sulfide	-	C	C	-	C	A	A	C	-	A	-	-	A	A	A	-	-	D	-	A	-	-	A	A	-	A	A	-	A	-	A	A	
Sodium Tetraborate	-	-	A	-	-	-	-	-	-	-	-	-	A	-	-	A	B	-	-	-	-	-	A	A	-	A	A	-	-	-	-	A	
Sodium Thiosulphate ("Hypo")	A	A	A	-	B	A	-	D	D	C	B	-	A	-	A	A	C	A	-	-	A	A	A	A	-	A	B	-	A	A	C	A	
Sorghum	-	A	A	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	-	-	-	A	A	-	A	A	-	A	-	-	A	
Soy Sauce	-	A	A	-	A	-	-	A	-	D	-	-	-	-	-	A	A	A	-	-	-	-	A	A	-	A	A	-	A	-	D	A	
Stannic Chloride	D	D	D	-	D	A	B	D	-	D	D	A	A	-	A	A	C	A	-	B	A	-	-	A	-	A	A	D	A	A	A	A	
Stannic Fluoborate	-	-	A	-	-	-	-	-	-	D	-	-	-	-	-	A	C	-	-	-	-	-	-	A	-	A	A	-	A	-	-	A	
Stannous Chloride	D	D	C	-	D	A	A	D	-	D	D	-	A	A	A	-	-	D	-	A	-	-	-	-	-	B	C	D	D	-	A	A	
Starch	B	A	A	-	A	-	-	B	-	C	C	-	A	-	A	A	A	A	-	B	-	-	A	A	-	A	A	-	A	-	-	A	
Stearic Acid ²	B	A	A	A	B	A	A	C	C	C	C	A	A	B	A	A	A	A	-	B	D	-	A	A	A	B	D	B	B	C	A		
Stoddard Solvent	A	A	A	A	A	A	A	A	A	B	B	A	A	D	A	D	A	A	B	D	D	A	A	A	-	A	B	D	D	D	D	A	
Styrene	A	A	A	-	A	-	-	A	-	-	A	-	-	-	A	A	A	-	-	-	-	-	A	A	-	B	D	D	D	D	D	A	
Sugar (Liquids)	A	A	A	A	A	-	A	A	-	B	B	-	-	-	A	A	A	A	B	-	A	-	A	A	A	A	A	-	B	-	A	A	
Sulfate Liquors	-	C	C	-	B	-	A	C	-	-	-	-	-	-	-	D	-	-	-	A	-	A	A	-	-	-	-	C	-	-	A		
Sulfur Chloride	-	D	D	D	D	-	-	C	D	-	-	-	A	C	A	A	D	A	-	A	D	-	A	C	-	A	D	-	D	D	D	C	
Sulfur Dioxide ²	-	A	A	C	A	A	B	B	-	-	-	B	D	B	A	D	B	D	D	C	D	A	A	A	-	D	D	C	B	A	D	A	
Sulfur Dioxide (dry)	A	A	A	-	A	-	A	A	C	A	B	-	D	-	A	-	-	A	-	D	-	-	A	A	-	D	-	-	D	-	D	D	
Sulfur Trioxide (dry)	A	A	C	-	A	-	-	B	-	B	B	-	A	B	A	D	D	D	-	-	-	-	B	A	-	A	D	-	D	B	C	A	
Sulfuric Acid (to 10%)	-	D	C	C	C	A	A	D	D	D	-	A	A	B	A	A	D	D	B	B	A	A	A	A	-	A	C	-	D	D	C	A	
Sulfuric Acid 10%-75% ²	-	D	D	D	D	C	B	D	D	D	-	A	A	B	A	B	D	D	B	C	A	B	A	D	C	A	D	-	D	D	D	B	
Sulfuric Acid 75%-100%	-	-	D	-	-	D	B	-	D	-	-	A	B	-	A	A	-	D	-	-	B	C	-	A	-	A	D	-	D	-	-	D	
Sulfurous Acid	C	C	B	C	C	A	B	D	-	D	D	-	A	B	A	A	D	D	-	B	A	-	B	A	-	A	C	D	B	B	C	A	
Sulfuryl Chloride	-	-	-	-	-	-	-	-	-	-	-	-	A	-	A	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	A	
Syrup	-	A	A	A	A	-	-	D	-	-	-	-	A	-	-	A	A	A	B	-	A	-	A	A	A	A	A	-	B	-	A	A	
Tallow	-	A	A	-	A	-	-	-	-	-	-	-	-	-	-	A	A	A	-	C	-	-	A	A	-	A	A	-	-	-	-	A	
Tannic Acid	B	A	A	A	C	A	B	B	-	C	C	A	A	B	A	A	B	D	-	B	A	-	A	A	A	A	D	C	A	A	A	A	
Tanning Liquors	-	A	A	-	C	A	A	A	-	-	-	-	A	B	A	-	B	-	-	-	A	-	A	A	-	A	C	-	-	-	-	A	
Tartaric Acid	B	A	B	B	C	A	B	A	C	D	D	A	A	B	A	A	B	A	-	B	A	-	A	A	-	A	D	C	A	-	A	A	

FOOTNOTES

- 1. P.V.C. - Satisfactory to 72° F.
- 2. Polypropylene - Satisfactory to 72° F.
- 3. Polypropylene - Satisfactory to 120° F.
- 4. Buna-N - Satisfactory for "O" Rings
- 5. Polyacetal - Satisfactory to 72° F.
- 6. Ceramag - Satisfactory to 72° F.

Chemical Resistance Chart

Tetrachlorethane - Zinc Sulfate

RATINGS - CHEMICAL EFFECT
A: No effect - Excellent
B: Minor effect - Good
C: Moderate effect - Fair
D: Severe effect - Not Recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminum	TITANIUM	HASTELLOY C	Cast Bronze	Brass	Cast Iron	Carbon Steel	KYNAR	PVC (Type 1)	Tygon (E-3606)	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	POLYPROPYLENE	RYTON	CARBON	CERAMIC	CERAMAGNET "A"	VITON	BUNA N (NITRILE)	Silicon	Neoprene	Ethylene Propylene (EPM)	Rubber (Natural)	Epoxy
Tetrachlorethane	-	-	A	-	-	A	A	-	-	-	-	-	D	-	A	D	A	A	-	-	A	-	A	A	-	A	D	-	-	D	D	A
Tetrahydrofuran	-	A	A	-	D	-	-	D	-	D	A	D	D	-	A	D	A	A	-	D	C	A	A	A	-	D	D	-	D	B	D	A
Toluene, Toluol ³	A	A	A	-	A	A	A	A	A	A	A	A	D	D	A	D	A	A	D	D	D	A	A	A	A	C	D	D	D	D	D	A
Tomato Juice	A	A	A	-	A	-	-	C	-	C	C	-	-	-	A	A	B	A	B	-	A	A	A	A	-	A	A	-	A	-	-	A
Trichlorethane	-	C	A	-	C	A	A	C	-	C	-	-	-	-	A	D	A	-	-	-	-	-	A	A	-	A	D	D	D	D	A	
Trichlorethylene ²	B	A	A	-	B	A	A	B	A	C	B	A	D	-	A	D	A	C	D	D	D	C	A	A	C	A	D	D	D	D	A	
Trichloropropane	-	-	A	-	-	-	-	A	-	-	-	-	-	-	-	D	A	-	D	-	-	-	A	A	-	A	A	-	A	-	-	A
Tricresylphosphate	-	-	A	-	-	B	A	A	-	-	-	-	D	-	A	A	C	-	-	-	-	-	A	A	-	B	D	-	D	A	-	A
Triethylamine	-	-	-	-	-	-	-	A	-	-	-	-	A	-	-	B	D	-	-	-	-	-	A	A	-	A	A	D	B	-	-	A
Turpentine ³	B	A	A	-	C	-	A	B	C	B	B	A	A	B	A	D	A	A	-	D	B	A	A	A	-	A	D	-	D	D	D	A
Urine	-	A	A	-	B	-	-	C	-	B	-	-	A	-	-	A	A	A	-	B	A	-	A	A	-	A	A	-	D	A	-	A
Vegetable Juice	-	A	A	-	A	-	-	C	-	D	-	-	-	-	-	A	A	A	-	-	-	-	A	A	-	A	A	B	D	-	D	A
Vinegar	A	A	A	A	D	A	A	B	B	C	D	A	A	-	A	A	B	A	B	B			C	-	B	A	C	A				
Varnish (Use Viton for Aromatic)	A	A	A	A	A	-	-	A	B	-	C	-	-	-	A	D	A	A	-	-	A	-	A	A	A	A	B	C	D	-	D	A
Water, Acid, Mine	-	A	A	-	C	-	-	C	D	C	-	-	A	B	-	A	D	A	B	-	A	B	A	A	-	A	A	-	B	-	B	A
Water, Distilled, Lab Grade 7	-	A	A	-	B	-	-	A	-	D	-	-	A	B	A	A	A	A	A	-	A	A	A	A	A	A	A	-	B	A	A	A
Water, Fresh	A	A	A	-	A	-	-	A	C	B	D	-	A	B	A	A	A	A	A	D	A	A	A	A	A	A	A	-	B	A	A	A
Water, Salt	-	A	A	-	B	-	-	B	C	D	-	-	A	B	-	A	A	A	-	-	A	A	A	A	A	A	A	-	B	A	A	A
Weed Killers	-	A	A	-	C	-	-	C	-	-	-	-	-	-	-	A	A	-	-	-	-	-	A	A	-	A	B	-	C	-	-	A
Whey	-	A	A	-	B	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	A	-	-	-	-	A
Whiskey & Wines	A	A	A	A	D	-	-	B	B	D	D	-	A	-	A	A	A	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A
White Liquor (Pulp Mill)	-	A	A	-	-	-	A	D	-	C	-	-	A	-	A	A	D	A	-	-	A	-	A	A	-	A	A	-	-	-	-	A
White Water (Paper Mill)	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	B	A	-	-	A	-	A	A	-	A	-	-	A	-	-	-	A
Xylene ²	A	A	A	-	A	-	A	A	A	B	A	D	-	A	D	A	A	D	D	D	D	A	A	A	A	A	D	D	D	D	D	A
Zinc Chloride	D	D	B	B	D	A	B	D	D	D	D	A	A	-	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	A	A
Zinc Hydrosulphite	-	-	A	-	D	-	-	D	-	D	-	-	-	-	-	A	C	-	-	-	-	A	A	A	-	-	A	-	A	A	-	A
Zinc Sulfate	B	A	A	A	D	A	B	B	C	C	D	A	C	B	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	C	A

FOOTNOTES

- 1. P.V.C. - Satisfactory to 72° F.
- 2. Polypropylene - Satisfactory to 72° F.
- 3. Polypropylene - Satisfactory to 120° F.
- 4. Buna-N - Satisfactory for "O" Rings
- 5. Polyacetal - Satisfactory to 72° F.
- 6. Ceramag - Satisfactory to 72° F.